

ECO-DRY ACTIVE

Quality and Finish	Hainsworth® Eco Dry Active	
Colour	Paris / Ecreu	
Composition	46% Nomex® 54% Wool/Lenzing	
Construction	Double Cloth	
Conditioned Weight (gsm)	220 +/- 5%	BS EN12127
Useable Width (cms)	≥ 158	BS EN 1773:1997
Tensile Strength Warp / Weft N	≥ 700 / 600	BS EN ISO 13934-1
Tensile Extension Warp / Weft %	≥ 13 / 14	BS EN ISO 13934-1
Tear Strength Warp / Weft N	≥ 70 / 75	BS EN ISO 13937-2
Washing Stability Warp / Weft %	≤ 3	ISO 5077 after 5 cycles To ISO 6330 (2A Pro E)
Abrasion Resistance 12KPa 2 Broken Threads	≥ 50,000	ISO 12947-2
Pilling	≥ 3-4	BS EN ISO 12945-2 4000 Cycles
Colour Fastness to Light	≥ 3	BS EN ISO 105 B02
Water Repellency	> 4	EN 24920
After Care	Wash at 60C Tumble Dry Hot - Do not bleach	



HAINSWORTH®
TECHNOLOGY

Spring Valley Mills, Stanningley, Pudsey, West Yorkshire LS28 6DW United Kingdom

hainsworthtechnology.co.uk

